

## Refractory Castable

Ariacast 55H

### Chemical Analysis

Al <sub>2</sub> O <sub>3</sub>	Min 56 %
Fe <sub>2</sub> O <sub>3</sub>	Max 2.1 %
CaO	Max 4.2 %

### Physical Properties

Grain Size	0 – 5 mm
Bulk Density	min 2.25 g/cm <sup>3</sup>
Mixing Liquid(water)	9 - 11 %
Cold Crushing Strength after drying at 110°C after firing at 1300°C	min 450 kg/cm <sup>2</sup> min 410 kg/cm <sup>2</sup>
Max. Service Temp.	1500°C
Strong Limit	6 months

### Packing

Packed In Proof Big Bags Of 1000 kg

### Note

*The above technical information represents average value established by DIN standard test procedure.*

*These data serves to give general information.*

*They are liable to natural deviations, depending on production and shape, and they are not to be considered as guaranteed properties or guaranteed values.*

آدرس کارخانه: اصفهان، کیلومتر ۲۰ جاده اصفهان - نائین

تلفن: ۰۳۱ ۳۸۷۸ ۲۹ ۴۵ فکس: ۰۳۱ ۳۸۷۸ ۲۹ ۴۶

Email : info@azarbanref.com