

## **Refractory Castable**

Ariacast 75

## **Chemical Analysis**

### $Al_2O_3$ Min 75.4 % $Fe_2O_3$ Max 1.6 %

CaO Max 4.2 %

# Physical Properties

Grain Size 0-5 mm

Bulk Density min 2.4 g/cm<sup>3</sup>

Mixing Liquid(water) 8 - 10 %

Cold Crushing Strength

after drying at 110°c min 580 kg/cm² after firing at 1300°c min 550 kg/cm²

Max. Service Temp. 1650°c

Strong Limit 6 months

# **Packing**

Packed In Proof Bags Of 25 kg

#### **Note**

The above technical information represents average value established by DIN standard test procedure.

These data serves to give general information.

They are liable to natural deviations, depending on production and shape, and they are not to be considered as guaranteed properties or guaranteed values.

أدرس كارخانه: اصفهان ، كيلومتر ٢٠ جاده اصفهان \_ نائيين

تلفن: ۵۴ ۲۹ ۳۸۷۸ ۳۹۰ فکس: ۴۶ ۲۹ ۸۷۸ ۳۸۱ ۳۸۰

Email: info@azarbanref.com