

1700°c

3 months

Refractory Castable

Ariacast 80Lc

Chemical Analysis

Physical Properties

Max. Service Temp.

Strong Limit

Al ₂ O ₃	Min 80 %	Grain Size	0 – 5 mm
Fe ₂ O ₃	Max 1.4 %	Bulk Density	min 2.4 g/cm ³
CaO	Max 2.2%	Mixing Liquid(water)	6 - 7 %
		Cold Crushing Strength after drying at 110°c after firing at 1300°c	min 900 kg/cm² min 1150 kg/cm²

Packing

Packed In Proof Bags Of 25 kg

Note

The above technical information represents average value established by DIN standard test procedure.

These data serves to give general information.

They are liable to natural deviations, depending on production and shape, and they are not to be considered as guaranteed properties or guaranteed values.

> اَدرس کارخانه : اصفهان ، کیلومتر ۲۰ جاده اصفهان _ نائیین تلفن : ۲۵ ۲۹ ۲۹ ۲۸۷۸ ۲۹ فکس : ۴۶ ۲۹ ۲۸۷۸ ۳۱۱ Email : info@azarbanref.com