

Refractory Castable

Ariacast 90Lc

Chemical Analysis

Al ₂ O ₃	Min 90.3 %
Fe ₂ O ₃	Max 0.5 %
CaO	Max 1.9 %

Physical Properties

Grain Size	0 – 5 mm
Bulk Density	min 2.6 g/cm ³
Mixing Liquid(water)	6 - 7 %
Cold Crushing Strength after drying at 110°C after firing at 1300°C	min 950 kg/cm ² min 1210 kg/cm ²
Max. Service Temp.	1800°C
Strong Limit	3 months

Packing

Packed In Proof Bags Of 25 kg

Note

The above technical information represents average value established by DIN standard test procedure.

These data serves to give general information.

They are liable to natural deviations, depending on production and shape, and they are not to be considered as guaranteed properties or guaranteed values.

آدرس کارخانه : اصفهان ، کیلومتر ۲۰ جاده اصفهان _ نائین

تلفن : ۰۳۱ ۳۸۷۸ ۲۹ ۴۵ فکس : ۰۳۱ ۳۸۷۸ ۲۹ ۴۶

Email : info@azarbanref.com