

0-3 mm

7 - 9 %

min 2.6 g/cm<sup>3</sup>

## **Refractory Castable**

Ariacast B.90

## **Chemical Analysis**

 $Al_2O_3$  Min 90.3 % Grain Size  $Fe_2O_3$  Max 0.7 % Bulk Density CaO Max 5.9 % Mixing Liquid(water)

Cold Crushing Strength

**Physical Properties** 

after drying at 110°c min 480 kg/cm² after firing at 1300°c min 460 kg/cm²

Max. Service Temp. 1800°c

Strong Limit 6 months

## **Packing**

Packed In Proof Bags Of 25 kg

## **Note**

The above technical information represents average value established by DIN standard test procedure.

These data serves to give general information.

They are liable to natural deviations, depending on production and shape, and they are not to be considered as guaranteed properties or guaranteed values.

أدرس كارخانه: اصفهان ، كيلومتر ۲۰ جاده اصفهان \_ نائيين

تلفن: ۵۶ ۲۹ ۳۸۷۸ ۳۱۰ فکس: ۴۶ ۲۹ ۸۷۸ ۳۱۰

Email: info@azarbanref.com